



wherein R^1 is a C_{1-12} alkyl group, a substituted alkyl group, an alkoxy group, an aryl group, a substituted aryl group or halogen; and n is an integer of 0 to 5 and, when n is 2 or more, the R^1 's may be the same or different:



wherein R^2 is a C_{1-30} alkylene group, a substituted alkylene group or a polyalkylene oxide glycol residue; R^3 is a C_{1-12} alkyl group, a substituted alkyl group, an alkoxy group, an aryl group, a substituted aryl group or halogen; and n is an integer of 0 to 5 and, when n is 2 or more, the R^3 's may be the same or different:



wherein R^4 is a C_{1-30} alkylene group; n is an integer of 0 to 20; and R^5 is a C_{1-30} alkyl group, a C_{2-20} alkenyl group or an alkynyl group.

5. (Amended) The composition according to claim 2, wherein the branched polyacetal copolymer (A) indispensably contains the cyclic ether compound (a-3) copolymerizable with trioxane and is a copolymerized product of 0.1 to 20 parts by weight of the compound (a-3) to 100 parts by weight of trioxane.
6. (Amended) The composition according to claim 2, wherein the cyclic ether compound (a-3) which is copolymerizable with trioxane is selected from the group consisting of ethylene oxide, 1,3-dioxolan, diethylene glycol formal and 1,4-butanediol formal.

Sub 5
B2
7. (Amended) The composition according to claim 1, wherein the polymer (B-1) is prepared from at least one olefin polymer (b-1), which are selected from the group consisting of polyethylene, polypropylene and an ethylene-propylene copolymer, and at least one vinyl polymer (b-2), which are selected from the group consisting of methyl polymethacrylate, an acrylonitrilestyrene copolymer and styrene.

A
8. (Amended) The composition according to claim 1, wherein the polymer (B-2) is a modified olefin polymer where 100 parts by weight of the olefin polymer (b-3) is modified with 0.1 to 20 parts by weight of maleic anhydride.

Sub 5
B2
9. (Amended) The composition according to claim 1, wherein the polymer (B-2) is a modified olefin polymer where at least one olefin polymer (b-3), which are selected from the group consisting of polyethylene, polypropylene, an ethylene-propylene copolymer, an ethylene-ethyl acrylate copolymer and an ethylene-methyl acrylate copolymer, is modified.

10. (Amended) The composition according to claim 1, wherein the lubricant (C) is at least one compound selected from the group consisting of silicone, an α -olefin oligomer, paraffin, a substituted diphenyl ether, derivatives of fatty acid having 10 or more carbons and derivatives of aliphatic alcohol having 10 or more carbons.